

SURAT TUGAS

Nomor: 1141-R/UNTAR/PENELITIAN/III/2022

Rektor Universitas Tarumanagara, dengan ini menugaskan kepada saudara:

1. **HENNY WIYANTO, Ir., M.T.**
2. **CHADIR ANWAR MAKARIM, Ir.,M.Sc.,Dr.,Prof.**
3. **ONNYXIFORUS GONDOKUSUMO, Ir., M.Eng., Dr.**

Untuk melaksanakan kegiatan penelitian/publikasi ilmiah dengan data sebagai berikut:

Judul	:	Condition Rating Examination Based on Visual Assessment of Concrete Damage Caused by Poor Implementation
Nama Media	:	Technology Reports of Kansai University
Penerbit	:	Kansai University
Volume/Tahun	:	Volume 62, Issue 09, October 2020
URL Repository	:	https://www.kansaiuniversityreports.com/volume/TRKU/62/09/condition-rating-examination-based-on-visual-assessment-of-concrete-damage-caused-by-poor-im

Demikian Surat Tugas ini dibuat, untuk dilaksanakan dengan sebaik-baiknya dan melaporkan hasil penugasan tersebut kepada Rektor Universitas Tarumanagara

02 Maret 2022
Rektor



Prof. Dr. Ir. AGUSTINUS PURNA IRAWAN

Print Security : f4fc8ba66c5316b28d2ba1dc673109b1

Disclaimer: Surat ini dicetak dari Sistem Layanan Informasi Terpadu Universitas Tarumanagara dan dinyatakan sah secara hukum.

Condition Rating Examination Based on Visual Assessment of Concrete Damage Caused By Poor Implementation

Henny Wiyanto¹, Chaidir Anwar Makarim², Onnyxiforus Gondokusumo³

Civil Engineering Doctoral Program, Universitas Tarumanagara - Jakarta, Indonesia^{1,2,3}



ABSTRACT— Concrete damage condition rating based on visual assessment is qualitative and subjective and depends on the investigator's experience, knowledge, and skills, which results in varied assessments from each investigator. To resolve this problem, a condition rating scale of visual-based concrete damage assessment has been developed in order to show a measured condition and rate the concrete damage conditions of buildings. The scale can describe buildings that are in very good to very bad condition; a very bad rating means that the building cannot be used. This assessment also calculates the building structure element's critical rating. The condition rating scale is determined based on the concrete's damage condition and the concrete's compressive strength requirements. Concrete damage-condition rating values are determined based on expert appraiser feedback that was obtained through a questionnaire, which was processed using the fuzzy logic approach. The condition rating scale usage of visual-based concrete damage assessment will show the building's structural element damage condition rating and the building damage condition rating as a whole, as well as the actions that need to be taken. Assessment results can also show a priority scale to determine the next actions to be taken by the decision-maker.

KEYWORDS: Condition Rating, Visual Assessment, Concrete Structure, Poor Implementation.

1. INTRODUCTION

The condition of a building's structure can be identified by performing a control inspection. A building's functionality depends heavily on control inspection. Lack of control will cause damage to the building at a faster rate and impact repair costs. The first step of control inspection is a visual assessment of the building's structure [1]. According to ACI 201.1R-08 [2] visual assessment is often used as the first step in the evaluation of a building's structure for continuous use or change, strength or deformation analysis, or to determine the need for maintenance and rehabilitation. SEI/ASCE 11-99 [3] declared that the condition of existing building materials is rated with a visual assessment method, a non-destructive examination evaluation, and a destructive examination, including field procedures and laboratory. [4], [5], declared that a visual assessment does not have a reference yet, so the assessment is done subjectively. [6], declared that a condition rating is a numeric indicator that can be used on building structures and is used to assign a ranking. An assessment is meant to evaluate an existing building structure's condition to ensure the adequate safety of its existing weight. There is no code that determines the condition rating's characteristics and category. A condition that is assessed with a visual assessment tends to be qualitative and is usually declared in vague linguistic terms such as —bad, | —good, | or —very good. | A condition that is declared in linguistic terms varies from person to person. Because of that, qualitative information that is obtained from a visual assessment is subjective and depends on the experience, knowledge, and skill of the investigator. A number of condition rating assessment scales have been developed all around the world to deal with this qualitative element. This scale usually provides a condition that can be measured in terms of damage and adequate repair needs. To perform a reliability assessment, a reference value is needed as a condition comparison scale. Because of that, the acceptable value of the building structure's reliability needs to be determined first [7]. The problem is how to

find the highest acceptable structure reliability level. This value can be determined from a target reliability level that is planned [8]. According to ISO 2394:2015 [9] reliability is the ability for a structure or a structural element to fulfill a specific requirement in carrying a planned workload according to the condition that is determined at a certain point. A structure has the correct reliability level if it fulfills the requirements and reaches a specific target level against the serviceability limit state, ultimate limit state, and structural integrity. According to SEI/ASCE 11-99 [3] assessment consists of data collection and analysis, evaluation, and a systematic recommendation about the part of the building that is affected by the suggested function. [10], said that a reliability assessment of an existing building structure can be done through two steps: first, a visual assessment and then a more detailed assessment through an assortment of examinations before concluding with a reliability assessment. Up until the examination, there are already a number of standards and manuals that can be examined and assessed for reference. But until now, there has been no standard reference or technical guidance for structural reliability. The consequence is a descriptive assessment without a quantitative reference that is clearly measured. This lack of clarity makes it difficult for the decision-maker to take responsibility for a building assessment's result. Therefore, a reference for visual assessment needs to be developed in the form of a condition rating assessment scale.

2. Concrete Damage Condition Rating Scale

A rating assessment scale for the concrete's condition is needed as a reference in performing a visual assessment. A condition rating scale is formed from multiple research studies. [11] in 1998, performed a condition rating assessment on bridge concrete damage to determine repair priorities. They used six damage levels based on rating values. [12], performed a damage assessment of structural components with five criteria levels. [13], performed a bridge condition assessment using four ratings, from very good to very bad, with a condition index rating. [14], [4], [5], [15], [16], performed a building concrete damage assessment using six ratings, from lowest (a condition that doesn't need repairs) to highest (a condition that needs treatment right away). [17], performed a rating assessment of a building's concrete damage risk with four categories from lowest (very bad) to highest (very good) with a value spectrum. [18], performed a bridge concrete condition assessment using four condition ratings with a bridge soundness score (BSS) value interval.

3. Concrete Damage Examination Based on Visual Assessment

Concrete damage on buildings can be interpreted as the existence of a concrete condition change related to concrete performance. This damage can be in the form of physical changes in the concrete that can be seen with the naked eye and concrete quality degradation that can be detected by performing an examination on the concrete body. These changes are caused by multiple factors, such as natural disasters, environmental conditions, inadequate construction, inappropriate building usage such as too much weight, a building function change, and inadequate or no maintenance. Building damage leads to high risk for the building's users. To identify the concrete damage on the building, an assessment of the concrete's condition is needed. Visual assessment is a good first step in identifying concrete damage. Visual assessment is a concrete surface assessment that identifies and defines multiple concrete conditions that can be seen by the naked eye. Visual assessment provides important information about the structure's function and endurance [2]. Damage that is usually detected includes cracking, leaching/staining, spalling, delamination, and efflorescence. Damage can develop further over time. The visual form is used to perform an assessment of damage based on a visual assessment [4], [5]. Visual assessment can be used in an investigation strategy to optimize the workload needed. Surface-cracking patterns, peeling, cracking, and other elements can function as important visual forms for the first damage assessment [14]. ACI 201.1R-08 [2] stated that the types of physical concrete damage are cracking, distress, and feature and texture phenomena relative to its development. SEI/ASCE 11-99 [3] stated that multiple concrete damage types are based on concrete physical conditions and iron reinforcement. [4], [5], stated that concrete damage types are based on concrete physical conditions, including

corrosion, alkali aggregate reactions, freeze-thaw attacks, sulfate attacks, acid attacks, and fatigue.

4. Concrete Condition Rating Assessment Method

The condition rating scale determination is based on concrete damage conditions and concrete compressive strength requirements, which are described from very good to very bad. Very good means that the building fulfills the planned concrete compressive strength requirements, while very bad means that the quality of the concrete is very low and that the building cannot be used anymore or must be demolished (Table 1). Concrete damage condition rating scale determination refers to ACI 228.23-13 [19], SEI/ASCE 11-99 [3], PBI [20], and SNI 2847:2013 [21], with consideration to a number of references, such as [12], [14], [4], [5], [15], [16], as well as feedback from expert appraisers.

Table 1 Concrete condition rating scale

Condition Rating	Description	Criteria	Measure
1	Very good	No damage	No repairs needed, but still needs maintenance
2	Good	Light damage	Needs reparation in the field of routine maintenance
3	Medium	Medium damage	Immediately needs further assessment or testing, and/or reparation
4	Bad	Heavy damage	Needs structure strengthening or weight reduction
5	Very bad	Very heavy/critical damage	Cannot be maintained or demolished

Each structural element has different critical risks according to the building structure element's function. Therefore, in this concrete damage condition rating assessment method, the critical weight for each structural element is determined, as seen in Table 2. The critical weight is determined based on opinions from feedback appraisers by considering references such as [14], [4], [5], [15], [16], [18], [17].

Table 2 Structure element critical weight

Structure Element	Critical Weight
Shear wall (sw)	1
Column (K)	1
Beam (B)	0,7
Plate (P)	0,5

The damage type that can be classified as a result of poor performance can be seen in Table 3. This concrete damage type identification refers to ACI 201.1R-08 [2], ACI 228.2R-13 [19], SEI/ASCE 11-99 [3], as well as feedback from building construction expert appraisers.

Table 3 Concrete damage types caused by poor performance

No.	Damage Type	Damage Criteria
1	Cracks are perfect or imperfect separations from concrete into two or more parts that result from a fracture.	

	Craze Crack	Random cracking that occurs in a soft manner or results in gaps on plaster surface, cement paste, mortar, or concrete.
	Crazing	A continuation from a craze crack that happens on the surface.
	D-Cracks	Cracks on concrete that are parallel to joints and angles.
	Hairline Crack	Thin cracks on concrete surface.
	Mapping Crack	Cracks that occur because of shrinkage caused by a dried concrete surface that is held by thicker concrete or concrete with no shrinkage.
	Random Cracks	Uncontrolled cracks that occur because of the cracks appear in multiple directions from a control joint.
	Transverse Crack	Cracks that happen transversally because of flexibility.
2	Delamination	Concrete separation occurs in a horizontal and parallel manner, usually on the concrete's surface. Very often found on bridge decks and floor plates in parking buildings.
3	Honeycomb	Void in the concrete caused by a lack of vibration during fresh concrete pouring, low and inadequate slump, or reinforcement tightness.
4	Pop-outs are separations of a small part of concrete due to internal pressure that causes thinning. Depression/concrete damage usually takes the form of a cone.	
	Pop-outs (small)	Up to 10mm (0.4") pop-out size
	Pop-outs (medium)	Between 10mm and 50mm (0.4" and 2") pop-out size
	Pop-outs (large)	Larger than 50mm (2") pop-out size
5	Scaling is matrix cement peeling near the surface. Scaling is part of the disintegration process.	
	Scaling (light)	Scaling occurs only on the mortar surface and doesn't cause rough aggregate visibility.
	Scaling (medium)	Scaling occurs on the mortar surface with 5mm to 10mm depth (0.2"-0.4") and exposes rough aggregate.
	Scaling (severe)	Scaling occurs on the mortar surface with 5mm to 10mm depth (0.2"-0.4"), and rough aggregate is eroded with 10mm to 20mm depth (0.4"-0.8")
	Scaling (very severe)	Scaling occurs on rough aggregate with deeper depth than 20mm (0.8")
6	Spalling is the fallout of concrete fragments, usually in the form of concrete shards.	
	Spall (small)	Circle or oval-shaped or elongated in other cases, with no more depth than 20mm (0.8") and 150mm (6").
	Spall (large)	Circle or oval-shaped or elongated in other cases, with more depth than 20mm (0.8") and 150mm (6").
7	Distortion	Dimension or shape change caused by design factor or poor implementation, excess weight, quake, expansion.

Table 3 Concrete damage types caused by poor performance (con.)

No.	Damage Type	Damage Criteria
-----	-------------	-----------------

8	Stratification	Segregation from too much water or vibration on the concrete, which horizontally forms a layer with soft material on top, causing the rough material to gravitate to the bottom.
---	----------------	--

The concrete damage condition rating value is determined based on feedback from expert appraisers through a questionnaire, which is processed with the fuzzy logic approach. Data processing refers to [14], [4], [5], [15], [22], [23], [24], [25]. The condition rating assessment is determined using the scale from Table 1 and the structural element critical rating using Table 2. Data processing is done with the following steps:

- Validation is performed by removing invalid data and negligible respondent opinion. Data is removed if:

$$R_i < (R_{i+1} \text{ and } R_{i-1}), \text{ then } R_i = 0,5 (R_{i+1} + R_{i-1}) \quad (1)$$

where R_i is the number of respondents at condition rating i (1, 2, 3, 4, 5).

Negligible respondent opinion is removed if:

$$R_i < 0,1 \sum_{i=1}^n R_i, \text{ then } R_i = 0 \quad (2)$$

where n is the highest condition rating (5).

- Data normalization uses the following formula:

$$\mu_i = \frac{R_i}{R_{i,\max}} \quad (3)$$

where μ_i is membership function at condition rating i .

- Concrete damage type condition rating is determined with the centroid method, which is as follows:

$$CI = \frac{\sum_{i=1}^n \mu_i i}{\sum_{i=1}^n \mu_i} \quad (4)$$

where CI is damage type condition rating, and i is condition rating.

- Building concrete damage condition rating is determined by performing the weighted average method by considering the structure element's critical weight.

$$SCI = \frac{\sum_{se=1}^e w_{se} CI_{se}}{\sum_{se=1}^e w_{se}} \quad (5)$$

where SCI is structural condition rating, W_{se} is structure element type critical weight, CI_{se} is structure element condition rating, and e is structure element type. Concrete damage condition rating description and criteria, as well as the treatment performed towards the assessed building, is determined using Table 1.

This concrete damage condition rating assessment validation is done by applying the concrete damage data that resulted from the investigation and existing building assessment by expert appraisers.

5. Results and Discussion

A questionnaire was made to determine the condition rating value for each concrete damage type. The resulting data is processed with the fuzzy logic approach to result in a condition rating value for each type of concrete damage resulting from poor implementation. Data validation can be seen in Table 4.

Table 4. Data validation

No.	Damage Type	Data Validation I					Data Validation II				
		1	2	3	4	5	1	2	3	4	5
1	Craze Crack	1	6	7	1	1	0	6	7	0	0
2	Crazing	0	5	8	3	0	0	5	8	3	0
3	D-Cracks	0	1	12	3	0	0	0	12	3	0
4	Hairline Crack	1	10	5	0	0	0	10	5	0	0
5	Maping Crack	0	2	11	2	1	0	2	11	2	0
6	Random Cracks	0	1	9	5	1	0	0	9	5	0
7	Transverse Crack	0	1	10	4	1	0	0	10	4	0
8	Delamination	0	0	12	4	0	0	0	12	4	0
9	Honeycomb	0	1	8	6	1	0	0	8	6	0
10	Pop-outs (small)	0	7	6	3	0	0	7	6	3	0
11	Pop-outs (medium)	0	3	10	2	1	0	3	10	2	0
12	Pop-outs (large)	0	1	9	5	1	0	0	9	5	0
13	Scaling (light)	1	7	8	0	0	0	7	8	0	0
14	Scaling (medium)	0	2	14	0	0	0	2	14	0	0
15	Scaling (severe)	0	2	10	4	0	0	2	10	4	0
16	Scaling (very severe)	0	0	8	7	1	0	0	8	7	0
17	Spall (small)	0	2	12	1	1	0	2	12	0	0
18	Spall (large)	0	0	9	6	1	0	0	9	6	0
19	Distortion	0	0	3	11	2	0	0	3	11	2
20	Stratification	0	0	2	10	4	0	0	2	10	4

The concrete damage condition rating is determined based on membership function for each damage type NS can be seen in Table 5.

Table 5. Concrete damage condition rating

No.	Damage Type	Membership Function (μ_i)					$\sum_{i=1}^n \mu_i i$	$\sum_{i=1}^n \mu_i$	CI
		1	2	3	4	5			
1	Craze Crack	0	0.86	1	0	0	4.71	1.86	2.54
2	Crazing	0	0.63	1	0.38	0	5.75	2.00	2.88
3	D-Cracks	0	0	1	0.25	0	4.00	1.25	3.20
4	Hairline Crack	0	1	0.5	0	0	3.50	1.50	2.33
5	Maping Crack	0	0.18	1	0.18	0	4.09	1.36	3.00
6	Random Cracks	0	0	1	0.56	0	5.22	1.56	3.36
7	Transverse Crack	0	0	1	0.4	0	4.60	1.40	3.29
8	Delamination	0	0	1	0.33	0	4.33	1.33	3.25
9	Honeycomb	0	0	1	0.75	0	6.00	1.75	3.43
10	Pop-outs (small)	0	1	0.86	0.43	0	6.29	2.29	2.75
11	Pop-outs (medium)	0	0.3	1	0.2	0	4.40	1.50	2.93

12	Pop-outs (large)	0	0	1	0.56	0	5.22	1.56	3.36
13	Scaling (light)	0	0.88	1	0	0	4.75	1.88	2.53

Table 5. Concrete damage condition rating (con.)

No.	Damage Type	Membership Function (μ_i)					$\sum_{i=1}^n \mu_i i$	$\sum_{i=1}^n \mu_i$	CI
		1	2	3	4	5			
14	Scaling (medium)	0	0.14	1	0	0	3.29	1.14	2.88
15	Scaling (severe)	0	0.2	1	0.4	0	5.00	1.60	3.13
16	Scaling (very severe)	0	0	1	0.88	0	6.50	1.88	3.47
17	Spall (small)	0	0.17	1	0	0	3.33	1.17	2.86
18	Spall (large)	0	0	1	0.67	0	5.67	1.67	3.40
19	Distortion	0	0	0.27	1	0.18	5.73	1.45	3.94
20	Stratification	0	0	0.2	1	0.4	6.60	1.60	4.13

The assessment is applied to a 16-year-old 45-floor apartment building. Based on the visual examination results, the concrete damage data on each building's structural elements are obtained. The building's condition is assessed by rating the concrete damage condition according to the CI value that is obtained from Table 5, by calculating the structural element critical weight according to Table 2, and by determining the building condition according to Table 1. The visual investigation and assessment results can be seen in Table 6.

Table 6. Building concrete damage condition rating assessment

Elemen Number	Damage Type	CI_{se}	Element		$w_{se} CI_{se}$
			se	w_{se}	
1	Honeycomb	3.43	B	0.7	2.401
2	Craze Crack	2.54	P	0.5	1.270
3	Spall (small)	2.86	P	0.5	1.430
4	Scaling (light)	2.53	P	0.5	1.265
5	Scaling (light)	2.53	P	0.5	1.265
6	Crazing	2.88	P	0.5	1.440
7	Delamination	3.25	P	0.5	1.625
8	Delamination	3.25	P	0.5	1.625
9	Crazing	2.88	P	0.5	1.440
10	Craze Crack	2.54	P	0.5	1.270
11	Crazing	2.88	P	0.5	1.440
12	Crazing	2.88	P	0.5	1.440
13	Crazing	2.88	P	0.5	1.440
14	Craze Crack	2.54	P	0.5	1.270
15	Craze Crack	2.54	P	0.5	1.270
16	Craze Crack	2.54	B	0.7	1.778
17	Craze Crack	2.54	P	0.5	1.270
18	Delamination	3.25	P	0.5	1.625
19	Delamination	3.25	P	0.5	1.625
20	Delamination	3.25	P	0.5	1.625
21	Craze Crack	2.54	B	0.7	1.778
22	Crazing	2.88	P	0.5	1.440
23	Delamination	3.25	P	0.5	1.625
24	Crazing	2.88	P	0.5	1.440
25	Crazing	2.88	P	0.5	1.440

Table 6. Building concrete damage condition rating assessment

Elemen Number	Damage Type	CI_{se}	Element		$w_{se}CI_{se}$
			se	w_{se}	
26	Craze Crack	2.54	B	0.7	1.778
27	Crazing	2.88	P	0.5	1.440
28	Scaling (light)	2.53	P	0.5	1.265
			Σ	14.8	42.02
			SCI		2.84

The concrete damage condition rating assessment results in Table 6 show that the building concrete damage condition rating is medium, with damage caused by poor implementation. The medium condition rating means that further investigation and repairs on some of the building's structural elements need to be implemented immediately. Validation towards assessment results is done by expert appraisers.

6. Conclusion

A building's condition rating based on visual assessment is usually achieved using a descriptive assessment that is qualitative and subjective and depends on the knowledge, experience, and skills of the investigator. A code that determines the concrete's damage condition rating does not yet exist. To resolve that, a condition rating scale to perform a rating assessment of the concrete damage condition is developed. This scale normally provides a measurable condition to determine a damage rating. The scale being developed here can accurately show a building's condition from best to worst, where worst is a building that cannot be used anymore. A condition rating from a visual assessment for each type of concrete damage is determined based on assessment from expert appraisers. To accommodate qualitative and subjective assessments, data processing is done with the fuzzy logic approach. Condition rating values that result from each type of concrete damage describe damage criteria. That condition rating can describe the building's structural element damage condition and building damage condition rating, as well as determine the action needed. Therefore, this condition rating value can be used to determine a priority scale for implementation between structure elements or between buildings. This concrete damage condition rating assessment based on visual assessment can be the base to implement further examination in the form of a non-destructive or a destructive examination of the assessed building structure.

7. References

- [1] Stochino, F., Fadda, M.I., and Mistretta, F. (2018). "Low Cost Condition Assessment Method for Existing RC Bridges." *Engineering Failure Analysis Journal*, Elsevier, 86, 56-71, April 2018., 2018.
- [2] American Concrete Institute (ACI) Committee 201. (2008). "Guide for conducting a visual inspection of concrete in service." ACI 201.1R-08, The American Concrete Institute, Farmington Hills, MI. USA.
- [3] Structural Engineering Institute American Society of Civil Engineers (SEI/ASCE). (2000). "Guideline for structural condition assessment of existing buildings." SEI/ASCE 11-99, The American Society of Civil Engineers, The United State of America.
- [4] Jain, K.K. and Bhattacharjee, B. (2012). "Visual inspection and condition assessment of structures (VICAS): an innovative tool for structural condition assessment." *International Journal 3R's*, 3(1), 349-357, Januari-Maret.
- [5] Jain, K.K. and Bhattacharjee, B. (2012). "Application of fuzzy concepts to the visual assessment of deterioration reinforced concrete structure." *Journal of Construction Engineering and Management*, 138(3),

399-408, March.

- [6] Comité Euro-International du Béton (CEB). (1998). "Strategies for Testing and Assessment of Concrete Structures. Guidance Report." CEB-FIP, Bulletin d' Information, 243, Switzerland.
- [7] Preiser, W.F.E. and Vischer, J.C. (2005). "Assessing building performance." Book ISBN 0 7506 6174 7, Elsevier Butterworth-Heinemann.
- [8] Rucker, W., Hille, F., and Rohrmann, R. (2006), "Guideline for the assessment of existing structure." Federal Institute of Materials Research and Testing (BAM), Berlin, Germany.
- [9] International Organization for Standardization (ISO). (2015). "General principles on reliability for structures." Standard ISO 2394:2015. 4th Edition.
- [10] Wuryanti, W. (2013). "Penilaian keandalan struktur bangunan gedung eksisting: peraturan dan implementasinya." Prosiding Konferensi Nasional Teknik Sipil 7 (KoNTekS 7), S69-75, Universitas Sebelas Maret (UNS), Surakarta.
- [11] Znidaric, J., and Perus, I. (1998). "Condition Rating Methods for Concrete Structures." CEB-FIP, Bulletin d' Information, Strategies for Testing and Assessment of Concrete Structure, Guidance Report. 243, 155-168, Switzerland, Mei 1998.
- [12] Amri, S. (2006). "Teknologi audit forensik, repair dan retrofit untuk rumah & bangunan gedung." ISBN:9791124000. Cetakan Pertama. Yayasan John Hi-Tech Idetama, Jakarta.
- [13] Abu, D.S. and Alkass, S. (2010). "A stochastic method for condition rating of concrete bridges." Construction Research Congress, 8-10 May 2010, Banff, Alberta, Canada.
- [14] Mitra, G., Jain, K.K., and Bhattacharjee, B. (2010). "Condition assessment of corrosion-distressed reinforced concrete buildings using fuzzy logic." Journal of Performance of Constructed Facilities, 24(6), 562-570, December.
- [15] Tirpude, N.P., Jain, K.K., and Bhattacharjee, B. (2014). "Decision model for repair prioritization of reinforced-concrete structures." Journal of Performance of Constructed Facilities, 28(2), 250-256, April.
- [16] Pragalath, H., Seshathiri, S., Rathod, H., Esakki, B., and Gupta, R. (2018). "Deterioration assessment of infrastructure using fuzzy logic and image processing algorithm." Journal of Performance of Constructed Facilities, 32(2), 1-13, April.
- [17] Malek, M., Tumeo, M., and Saliba, J. (2015). "Fuzzy logic approach to risk assessment associated with concrete deterioration." ASCE-ASME Journal of Risk and Uncertainty in Engineering Systems, Part A: Civil Engineering, 1(1), 1-8, March.
- [18] Pushpakumara, B.H.J., Silva, S., and Silva, G.H.M.J.S. (2017). "Visual inspection and non-destructive tests-based rating method for concrete bridges." International Journal of Structural Engineering, 8(1), 74-91.

- [19] American Concrete Institute (ACI) Committee 228. (2013). "Report on nondestructive test methods for evaluation of concrete in structures." ACI 228.2R-13, The American Concrete Institute, Farmington Hills, MI. USA.
- [20] Direktorat Penyelidikan Masalah Bangunan. (1979). "Peraturan beton Indonesia." PBI N.I.-2 1971, Cetakan ke-7 tahun 1979. Direktorat Jenderal Cipta Karya, Departemen Pekerjaan Umum dan Tenaga Listrik, Jakarta.
- [21] Badan Standarisasi Nasional (BSN). (2013). "Persyaratan beton struktural untuk bangunan gedung." Standar Nasional Indonesia (SNI) 2847-2013, Jakarta.
- [22] Kusumadewi, S dan Purnomo, H. (2010). "Aplikasi logika fuzzy untuk pendukung keputusan." Edisi Kedua. Graha Ilmu. Yogyakarta.
- [23] Ross, T.J. (2010). "Fuzzy Logic with Engineering Applications." Third Edition. John Wiley & Sons, Ltd. UK.
- [24] Wang, L.X. (1997). "A Course in Fuzzy Systems and control." International Edition. Prentice-Hall International, Inc. USA.
- [25] Zadeh, L.A. (1972). "A Fuzzy-Set-Theoretic Interpretation of Linguistic Hedges." Journal of Cybernetics and Systems, 2(3), 4-34.



This work is licensed under a Creative Commons Attribution Non-Commercial 4.0 International License.