



an Open Access Journal by MDPI



Certificate of publication for the article titled:

An Experimental Investigation into Mechanical and Thermal Properties of Hybrid Woven Rattan/Glass-Fiber-Reinforced Epoxy Composites

Authored by:

Agustinus Purna Irawan; Paula Tjatoerwidya Anggarina; Didi Widya Utama; Najid Najid; Mohd Zulkfly Abdullah; Januar Parlaungan Siregar; Tezara Cionita; Deni Fajar Fitriyana; Jamiluddin Jaafar; Agung Efriyo Hadi; Teuku Rihayat

Published in:

Polymers 2022, Volume 14, Issue 24, 5562



Academic Open Access Publishing since 1996

Basel, December 2022





Article An Experimental Investigation into Mechanical and Thermal Properties of Hybrid Woven Rattan/Glass-Fiber-Reinforced Epoxy Composites

Agustinus Purna Irawan ^{1,*}, Paula Tjatoerwidya Anggarina ², Didi Widya Utama ¹, Najid Najid ¹, Mohd Zulkfly Abdullah ³, Januar Parlaungan Siregar ^{4,*}, Tezara Cionita ⁵, Deni Fajar Fitriyana ⁶, Jamiluddin Jaafar ⁷, Agung Efriyo Hadi ⁸ and Teuku Rihayat ⁹

- ¹ Faculty of Engineering, Universitas Tarumanagara, Jakarta 11480, Indonesia
- ² Faculty of Economics and Business, Universitas Tarumanagara, Jakarta 11480, Indonesia
- ³ School of Mechanical Engineering, Engineering Campus, Universiti Sains Malaysia, Nibong Tebal 14300, Malaysia
- ⁴ Faculty of Mechanical & Automotive Engineering Technology, Universiti Malaysia Pahang, Pekan 26600, Malaysia
- ⁵ Faculty of Engineering and Quantity Surveying, INTI International University, Nilai 71800, Malaysia
- ⁶ Department of Mechanical Engineering, Universitas Negeri Semarang, Kampus Sekaran, Semarang 50229, Indonesia
- ⁷ Faculty of Mechanical and Manufacturing Engineering, Universiti Tun Hussein Onn Malaysia, Parit Raja 86400, Malaysia
- ^b Mechanical Engineering Department, Faculty of Engineering, Universitas Malahayati, Jl. Pramuka No. 27, Kemiling, Bandar Lampung 35153, Indonesia
- ⁹ Department of Chemical Engineering, Politeknik Negeri Lhokseumawe, Lhokseumawe 24301, Indonesia
- Correspondence: agustinus@untar.ac.id (A.P.I.); januar@ump.edu.my (J.P.S.)

Abstract: The investigation of hybrid, woven, natural fiber-reinforced polymer composites as a substitute reinforcement for fiber polymer composites has recently caught the interest of academics, industry, and researchers. Woven, natural fiber composites have been implemented in many different applications, including parts for automobiles, household items, flooring, aerospace, and ballistic materials. Therefore, this research seeks to establish the thermal and mechanical characteristics of composites made from rattan strips (RS) and glass fiber (GF)-reinforced epoxy resin (ER). Other than that, the impact of layering configurations with respect to the thermal and mechanical characteristics of the RS and GF will be determined. Hand lay-up and a hydraulic press machine produce hybrid, woven RS and GF laminates. The hybrid composite's mechanical properties will be investigated using impact, tensile, and flexural tests. The hybrid woven of the GF/RS/RS/RS/GF composite sequence demonstrated the highest mechanical properties in comparison to other sequences. The increase from one to three layers of RS in the core layer of GF hybrid composites enhanced the flexural, impact, and tensile properties. In addition, the hybridization of rattan and GF is more thermally stable, as recorded by the high decomposition temperature. As a finding of the research, the woven RS and GF hybrid is a potential for automotive applications such as car bumpers, for example.

Keywords: rattan strips; woven; glass fiber; hybrid; composite

1. Introduction

In fiber-reinforced polymer composites, natural fibers exist in various forms, including continuous, random, and fabric [1]. According to Aisyah et al. (2021), woven composites comprise textiles with the maximum stability and flexibility [2]. In addition, woven fabrics are desirable as reinforcements due to their high level of integrity and conformability [3,4]. The purpose of woven textiles is to suit the needs of their intended receiver. During the previous 10 years, the utilization of woven, natural fibers as a substitute for synthetic



Citation: Irawan, A.P.; Anggarina, P.T.; Utama, D.W.; Najid, N.; Abdullah, M.Z.; Siregar, J.P.; Cionita, T.; Fitriyana, D.F.; Jaafar, J.; Hadi, A.E.; et al. An Experimental Investigation into Mechanical and Thermal Properties of Hybrid Woven Rattan/Glass-Fiber-Reinforced Epoxy Composites. *Polymers* **2022**, *14*, 5562. https://doi.org/10.3390/ polym14245562

Academic Editor: Keon-Soo Jang

Received: 3 November 2022 Accepted: 14 December 2022 Published: 19 December 2022

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



Copyright: © 2022 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (https:// creativecommons.org/licenses/by/ 4.0/). materials has increased in importance, accompanied by rapid development [5,6]. The increasing number of investigations into woven, natural fiber-reinforced polymer composite (W-NFRPC) materials, as depicted in Figure 1, indicates that the appealing qualities of composite materials have captured the attention of numerous researchers, academicians, and companies around the globe.



Figure 1. The number of research articles from 2010 to 2020 using the keyword woven, natural fiber-reinforced polymer composite (W-NFRPC).

The qualities of finished woven fiber-composite products are controlled by variables such as fiber type, fiber content, fiber layering, fiber stacking sequence, and fiber moisture content, all of which have a substantial effect on W-NFRPC processing. There are several factors that affect the mechanical and physical characteristics of woven, natural fiber composites, and multiple pieces of research have reported their outcomes [7,8]. Researchers have undertaken several initiatives to enhance the mechanical properties of W-NFRPC, for example, by the use of a hybridization method between natural woven fiber and synthetic fiber. The performance of hybrid composites can be considered as the weighted sum of the individual components, with the purpose being to find a more positive balance between the inherent benefits and drawbacks of each component. When utilizing a hybrid composite consisting of two or more distinct types of fiber, the benefits of one type of fiber may enhance what is lacking in another type of fiber. As a direct result of this, it is possible, via the utilization of an appropriate material design, to achieve a good balance between cost and performance [9,10]. When compared to the results obtained from hybridizing a natural fiber with a natural fiber in a composite, the hybridized composite of high-strength synthetic fibers, for example, carbon fiber and glass fiber (GF), with a natural fiber produced excellent mechanical properties [11].

There are a growing number of reviews and research articles investigating the effects of hybridization with respect to the performance of synthetic fiber and W-NFRPC for automotive applications, such as automobile bumper beams [12–18]. The primary purpose of a bumper system is to protect the vehicle's body and passengers from collision damage. The main components of a front bumper system are the bumper beam, the absorber, and the fascia [19]. Note that most polymer composites that were created for bumper beam materials were studied for the material's mechanical properties, which include its flexural properties (modulus and strength), tensile properties (modulus and strength), and impact characteristics [10].

Davoodi et al. (2010) developed and tested the mechanical properties of a synthetic GF and hybrid kenaf fiber-reinforced epoxy composite for passenger automobile bumper beams. Utilizing a sheet molding compound (SMC) method, hybrid materials were produced. The results of their investigation indicate that the flexural and tensile properties

of hybrid kenaf/GF are greater than those of conventional bumper beam materials, such as glass mat thermoplastics (GMT). Meanwhile, the impact energy of hybrid kenaf/GF was determined to be 26 J/m, almost half that of the typical GMT [16]. Other than that, the mechanical properties of jute and GF composites for car bumper beams were evaluated by Olorunnishola et al. (2018). Hand lay-up composites were created by laying the composites on the bumper mold along with commercial-grade polypropylene spraying. The samples underwent a 24 h post cure, and the surface was finished with a grinding wheel. Subsequently, three examples were made using 40% wt GF, 40% wt jute fiber, and 10% wt. GF with 30% wt. jute fiber. Apart from that, a maleated polypropylene (MAPP) compatibilizer was used to provide bonding between the polymer and the fibers. A universal testing machine was utilized to assess hardness and impact qualities, whereas a Charpy V-notch machine was employed to identify impact energy. Moreover, the hybrid model outperformed the commercial bumper material in terms of hardness and impact resistance [20].

Maisuriya et al. (2020) investigated the flexural and tensile properties of banana fiber/glass-reinforced polyester hybrid composites manufactured via the hand lay-up process. According to the study's findings, adding GF to composite materials improves both the flexural and tensile properties of the materials. Per the results, the flexural modulus and strength were both raised when the percentage of GF increased from 0 to 30 wt.%, increasing the MPa from 41.1 to 168.3 and the GPa from 1.3 to 5.7, respectively. Similarly, hybrid composites consisting of 20% banana and 20% GF achieved maximum values of 152.3 MPa and 4.0 GPa for their tensile strength (TS) and modulus, respectively [21]. Santhanam et al. (2021) investigated the impact of a five-layer stacking sequence of hybrid banana and GF-reinforced epoxy composite. The TS of the epoxy reinforced with banana fiber was 37.2 MPa, but hybridization with GF enhanced the TS to 84 MPa. The TS of specimens G-B-B-G and B-G-B-G-B were closer to each other, as were the tensile strengths of specimens B-G-G-G-B and G-B-G-B-G, indicating that variation in the stacking sequence has little impact on the tensile strength. Furthermore, the impact test findings show that the stacking sequence has no effect. However, hybridization of the banana fiber composite yielded higher values compared to pure banana fiber composites. The pure GF-reinforced epoxy composite possesses the highest impact strength value. Hence, hybridization enhanced the value of impact strength by 54% [22].

On the other hand, Gujjala and colleagues (2014) investigated the mechanical properties of a hybrid jute/glass-reinforced epoxy composite. Various stacking sequences of woven hybrid composite laminates were arranged by utilizing the hand lay-up technique. Furthermore, the modulus and TS of glass/jute/jute/glass (GJJG)-staked hybrid jute and glass are greater than those of GJGJ, JGGJ, and pure JJJ. The incorporation of GFs substantially raises the TS of pure jute laminate by 66% (GJJG), 51% (GJGJ), and 41% (JGGJ). The GJGJ hybrid composite established the greatest flexural modulus and flexural strength [23]. Alternatively, Ramnath et al. (2013) fabricated and evaluated the mechanical properties of an abaca–jute–GF-reinforced epoxy composite. GF is laminated onto the top and bottom of the composite, improving the polish and adding strength. The tensile strengths of hybrids made of glass, banana, and jute are 85.9 MPa, 68.4 MPa, and 51.1 MPa, respectively, per Ramnath. The jute/glass hybrid composite has the lowest TS compared to the other hybrid composites. In related research, jute/GF-reinforced polyester hybrid composites exhibited the highest impact strength at 752 J/m, in comparison to jute/banana/glass hybrids' 326 and 500 J/m values [24].

The number of layers within a woven, natural fiber laminate affects the mechanical as well as physical properties of composites made of woven, natural fiber [25]. According to Bhoopathi et al., 2014 studies, the stacking sequence affects the flexural strength result, with three layers of GF, as well as two layers of banana fiber, generating much better results than the hand lay-up of two layers of GF and three layers of banana fiber [26]. Acharya (2014) assessed the consequences of a layered stacking sequence with respect to the mechanical characteristics of treated jute and a hybrid GF-reinforced epoxy composite. A four-layered

stack of glass/jute/jute/glass possessed the greatest flexural strength and TS [27]. On the other hand, Yahaya et al. (2015) examined the woven kenaf–aramid hybrid laminated composite's mechanical properties. They reported that the four-layer hybrid composite outperformed the three-layer samples with regard to TS [28]. Similarly, Rajesh et al. (2018) found that four layers of jute basket-weaving fabric resulted in superior qualities compared to other weaves [29]. The experiment was conducted by Rajesh and Pitchaimani (2017), and Acharya (2014) utilized a four-layer stacking sequence. The results revealed that four fiber layers greatly increase the mechanical properties compared to three fiber layers [4,27].

In the aforementioned literature, the impacts of a hybrid of woven, natural fiber and synthetic fiber on the mechanical properties of an epoxy composite for bumper beam application have been reviewed. This research aims to examine the thermal and mechanical properties of hybrid, woven rattan/GF-reinforced epoxy composites. In addition, the influence of the layering number of RS and the hybrid on the tensile, impact, and flexural properties will be identified and compared. Furthermore, using thermogravimetric analysis (TGA), the excellent mechanical properties of pure and hybrid composite specimens will be observed for their thermal properties. The result of this study is expected to demonstrate the capability of fabricating competitive hybrid rattan strip with glass fiber (HRS/GF) reinforced ER composites that might be used as a replacement material for the automobile industry, particularly for bumper applications.

2. Materials and Methods

2.1. Materials

For this research, Manau rattan from Kalimantan, Indonesia, was utilized as a woven reinforcement. The outside layer (bast) of Manau rattan was cut to a diameter of 4 mm. The 30 cm \times 30 cm woven rattan strips (RS) were made in the traditional way at the materials laboratory at the University of Tarumanagara in Indonesia. The bi-directional E-GF and epoxy resin (ER) for general use (Epikote 828) were bought from the IZE solution (Selangor, Malaysia). The thermal and mechanical properties of the epoxy matrix and reinforcement are presented in Table 1.

Table 1. Thermal and mechanical properties of epoxy, rattan, and glass fiber [30–34].

Properties	Epikote 828	Rattan	E-Glass Fiber
Density (g/cm^3)	1.16	0.45	2.55-2.6
Initial viscosity @ 25 °C (Pa s)	<10-12	-	-
Modulus (GPa)	3	4.97	72–85
Tensile strength (MPa)	60	41.97-121.5	1900-2050
Elongation at break (%)	4	-	1.8-4.8
Glass transition (°C)	155	-	-

2.2. Fabrication of Composite Laminates

The composite laminate production was accomplished by employing a hand lay-up process. In order to hinder the composite plate process from sticking to the interior surface of the mold and facilitate removal, wax or a releasing agent was sprayed on it first. After manually combining the ER and hardener in a ratio of 3:1 for 5 min, the resin was manually poured into the mold, and the RS was laid on top of the resin. This process was continued until the appropriate layer was attained, where the tolerance for fabric alignment should also be considered. For the curing procedure, the mold was laid out at room temperature for 24 h. In the desired sequence, both pure and hybrid composite laminates are listed in Table 2. The layering number of RS from 1 to 4 layers and hybrid RS with glass fiber (GF) from 3 layers to 6 layers will be examined in this study. The outer skin (top and bottom) of the woven RS was composed of 2 layers of GF. Figure 2 shows the fabrication process of composite laminates and specimen tests.

	Configuration Model and Label Code	
Layering Number	Rattan Strip	Hybrid Rattan Strip
1	RS1	-
2	RS2	-
3	RS3	HRS3
4	RS4	HRS4
5	-	HRS5
6	-	HRS6

 Table 2. Configuration model and label code of specimen test.



Figure 2. Fabrication process and specimen test for composite laminates.

2.3. Tensile Test

To assess tensile properties, which include the tensile strength (TS) as well as tensile modulus (TM), specimens according to the ASTM D 638–IV standard were prepared. Using an INSTRON 3369 (INSTRON, Boston, MA, USA) universal instrumentation, a tensile test was conducted at a crosshead speed of 2 mm/min. Moreover, the TS and TM average values were determined based on seven specimens manufactured for each composite configuration type before testing.

2.4. Flexural Test

Utilizing the universal testing apparatus INSTRON 3369 (identical to tensile testing procedures), a three-point bending test is employed to analyze flexural strength and flexural modulus. Note that 127×12.7 and 3 mm were utilized to fabricate the specimen in accordance with ASTM D790-17 standard method. For each type of specimen test, seven replications were undertaken, and the average data were calculated.

2.5. Izod Impact Test

The Izod impact tests were conducted with Zwick Roell (Zwick Company, Ulm, Germany) and 10 J of impact energy. This test was conducted at room temperature under ASTM D256 standard method. The impact energies were determined through testing. The impact unnotched specimen dimensions were $63.5 \times 12.7 \times 3$ mm.

2.6. Scanning Electron Microscopy (SEM)

In both pure and hybrid rattan strip (HRS)-reinforced epoxy composites, in order to analyze the fracture and surface morphological behavior of tensile fracture specimens, a Hitachi TM3030 Plus (Hitachi, Tokyo, Japan) scanning electron microscope was employed. Using double electrically conductive carbon adhesive tapes, the samples were first sputter-coated with a thin palladium layer to avoid surface charge before being mounted on a scanning electron microscopy (SEM) holder. The samples were then evaluated using a microscope with magnifications of $50 \times$ and $100 \times$, having a 10 kV acceleration tension.

2.7. Thermogravimetric Analysis (TGA)

The thermal stability of composite filler composites with treated and untreated fillers was assessed using the Hitachi STA7200 thermogravimetric analyzer (Hitachi, Fukuoka, Japan). A 10 mg powdered sample was put in an alumina crucible before being kept in the furnace. The study was done in a controlled environment with nitrogen gas flowing

at a rate of 20 mL/min. Here, 10 $^{\circ}$ C/min was the constant temperature change rate. The experiment was conducted between 30 and 700 $^{\circ}$ C.

2.8. Differential Scanning Calorimetry (DSC)

A differential scanning calorimetric (DSC) analysis of composites was conducted utilizing a Perkin Elmer DSC 8000 (Perkin Elmer, MA, USA). The test was conducted using 20 mL/min of nitrogen flow and a 10 °C/min heating rate up to 350 °C above room temperature.

3. Results and Discussion

3.1. Tensile Properties

Figure 3 depicts the tensile modulus (TM) as well as the tensile strength (TS) of woven rattan strips (RS) and the hybrid RS with glass fiber (GF)-reinforced epoxy resin (ER) composites. Figure 3 shows that the maximum tensile stress occurred at RS3 and gradually decreased at RS4. This is because, as the number of woven RS rises, the resin concentration decreases, leaving insufficient resin to transfer the load between fibers. In addition, the resin is insufficient to cover the fibers, yielding a drop in TS as the fiber content increases [35]. Since it is described as the slope of the stress-strain curve in the elastic deformation region, the TM of the composites, as illustrated in Figure 3, behaves similarly to the TS. When reinforced with woven RS, the elastic modulus of the pure epoxy composite rose to roughly 1.30 GPa. Similar to the tensile strength, the composite's TM reaches its maximum value (1.77 GPa) in the RS3 specimen and decreases in the RS4 specimen. As the number of RS utilized in RS4 increased, the TM of the composite decreased. This could be attributed to the usage of rattan woven strips in RS3, which provide the strongest interfacial adhesion to the composite, resulting in an excellent load transfer [36]. However, the more rattan woven strips used in RS4 resulted in low interfacial adhesion, because the amount of ER used was insufficient to cover all areas of the woven rattan strips. Furthermore, the hemicellulose content of the composite increased as the number of woven RS used increased.



Figure 3. Tensile properties of epoxy composites reinforced with woven rattan strips.

The higher the hemicellulose concentration is, the more moisture is absorbed, resulting in a significant decrement in TM as well as TS [37]. The TM illustrates a similar pattern compared to the TS discovered in research performed by Ramanaiah et al. (2013). Consequently, their results presented that the TM and TS of the composite rose as the fiber content did [38]. Per a study by Sharba et al., the TM and TS in the plain-woven, glass-reinforced unsaturated polyester (UP) hybrid composite specimens exhibited a similar pattern [39]. Agustinus and Sukania [40] found that the average TS of laminated rattan strips with ER is about 24.57 MPa. Based on their study, it can be concluded that rattan fiber is an alternative material for making car spoiler applications [40]. This study conceded that the composites' tensile properties are determined by a variety of factors, which includes the type of reinforcement and matrix, the number of layers present, and the matrix and the fibers' interfacial bonding [41].

The tensile fracture of hybrid composites was examined utilizing scanning electron microscopy (SEM). Figure 4 portrays the fractured tensile specimens of the RS composite that was examined. Note that a crucial component of composite materials is the interfacial bonding that progresses between the fiber reinforcement and the resin matrix, resulting in a higher TS of the composite. Failure mechanisms, including matrix cracking, delamination, fiber breakage, and fiber pull-out, can have an influence on the woven fiber composites' mechanical properties [42]. Note that the micrograph of tensile fractured RS1 showed delamination on the specimen. The delamination in composites caused by inadequate interfacial bonding between the fiber and matrix resulted in a poor load transfer between the RS layers. Natural fibers are typically coated with waxy elements; this surface has low surface energy, resulting in poor adhesion to the polymer matrix [43]. Other than that, the crack-propagation mechanism is found in all the tensile fractured specimens. The fracture of the composites, which frequently comes from the creation of displacement discontinuity surfaces inside the composites, is the main cause of crack propagation. A fracture is when tension causes an object or material to split into two new pieces. Subsequently, the mechanism by which a crack spreads within composite materials by cutting through the structure's grain grains is known as a transgranular fracture. Meanwhile, intergranular fractures develop along grain boundaries [44,45].





Figure 4. Tensile fracture specimen of epoxy composites reinforced with rattan strips.

A hybrid material combines two or more materials to produce a novel substance that possesses new characteristics and behaviors. Compared to the properties of composites made from individual fibers, the hybrid composite had superior mechanical properties [46]. Figure 5 displays the effect of one to four layers of hybrid rattan strips (HRS) mixed with two plies of GF in the outermost layers on the composite's tensile properties, as determined by earlier research. [23,47]. Apart from that, TS and TM increased dramatically as the number of the hybrid layers was raised up to five. Here, the maximum TS and modulus of HRS5 or the combination of three layers of RS (RS3) and two plies of GF are 100.40 MPa and 3.7 GPa, respectively. The addition of two plies of GF to the outer layer of a single RS increased its TS from 36.50 MPa to 72.50 MPa. Comparing RS3 to RS1 with two layers of GF (HRS3), the hybrid composite possesses roughly 88%, which is higher in TS. In addition, the HRS3 composite's TM is 77% more than that of three layers of RS. The addition of GF

increases the strength and stiffness of hybrid composites due to their greater TS and TM, which are around 1900–2050 MPa (TS) and 72–85 GPa (TM) compared to 41.97–121.5 (TS) and 4.97 GPa (TM) for RS (see Table 1). In addition, the incorporation of GF into RS composites enhances the load-bearing ability of the hybrid composites, yielding increased strength and rigidity. This is a result of the excellent stress transfer between the RS plies and GF plies, enabling the hybrid composites to endure a higher tensile load. This pattern is consistent with the research conducted by Hariharan and Khalil [48], who worked on oil palm fiber–GF-reinforced ER. A previous study found that the TS of a single RS from four different species ranges from 464 to 603 MPa. In the meantime, the TM of a single RS is between 9.10 and 10.61 GPa [49]. Meanwhile, the tensile properties of GF are higher than those of natural fiber, as reported in previous studies [50,51]. In research comparing pure and hybrid, woven jute composites, GF had a higher specific strength than a natural fiber, and composites demonstrated more improvement when placed at the skin's outer surface than when placed in the composites' core [47]. Utilizing a hybrid composite made up of two or more different types of fibers might allow the advantages of one type of fiber to outweigh those of another [52].



Figure 5. Tensile properties of hybrid, woven rattan strips with glass fiber composites.

The HRS composite samples with various layer configurations experienced a tensile fracture, as seen by the micrograph of the fractured tensile specimen in Figure 6a-d. Observations of fractured specimens revealed that the failure of a RS composite occurs promptly with little fiber pull-out (Figure 4). Still, failure in HRS is regulated by a substantial fiber pull-out and cracking matrix, as shown in Figure 6a–d. During tensile testing, the exterior layers of composites composed of GF may have absorbed the stress and distributed it throughout the composites. Prior to failure, the RS at the core of the composite is subjected to less stress. The tensile properties of a hybrid composite are identified by the amount of fiber present, the arrangement of the individual fibers, and the degree to which the fibers are intertwined, along with the interfacial adhesion that is present between the fiber and the matrix [53,54]. Figure 6c depicts GF fiber fracture (breakage) and matrix cracking. The fiber breaking indicates that the configuration of HRS5 strength increased due to the incorporation of GF with RS in the epoxy composite, which is supported by the results shown in Figure 5. Matrix cracking occurred during the tensile test due to the brittleness of the epoxy resin [23]. Furthermore, based on the fiber-breakage phenomenon, the stress was efficiently transferred from the matrix to the woven fiber. As a result, woven fiber serves as an effective reinforcement in composites. However, in the HRS6 fractured sample with two layers of GF and four layers of RS, an occurrence of whole fiber pull-out was observed. Decreased matrix composition has resulted in weak interfacial adhesion between the fiber and matrix. The woven fiber and matrix, therefore, have poor interfacial adhesion [5]. As a result, our evidence supports the HRS6 sample's low TS values when compared to those of other samples.



Figure 6. Tensile fracture specimen of hybrid rattan strips with glass fiber composites.

3.2. Flexural Properties

The flexural characteristics of pure and HRS composites are shown in Figure 7a,b. Similar to TS, the inclusion of a layer of RS significantly boosted the flexural strength of the composites. Flexural modulus and strength rose by up to 22.2% and 41.5%, respectively, as the rattan layer was increased by up to four layers. However, the RS4 result indicates a decrease in flexural strength compared to the RS3 result. Therefore, the results of this study show that compared to virgin ER, RS3 possesses the highest TS and TM (Figure 7a). On top of that, the outcomes of flexural strength and the modulus for the HRS composite sample also present the highest result at HRS5, where the sample consists of two layers of GF and three layers of RS, as shown in Figure 7b. The HRS5 result shows an enhancement of 269% in flexural strength and 321% in flexural modulus, compared with the RS3 samples' result. This is due to the GF woven located at the bottom and top of the composite's reinforcement configuration, which is vital in transferring the stress applied to the composite sample. Theoretically, hybrid composite types consist of sandwich, intra-ply, and inter-ply composites. To create lightweight structures, sandwich-type hybrid composites typically consist of two or more distinct layers. This design is commonly employed to support bending loads (the core is constructed of lightweight material, for example, natural fiber, while the skins are composed of high-strength fiber-composite materials) [55,56]. This study shows that the RS composite has a lower strength and stiffness property than the GF composite because it cannot endure the applied load transferred from the epoxy matrix, given the poor interfacial adhesion between the RS and epoxy matrix as well as the RS's weak nature. Principally, the tensile and compressive conditions of the composite sample are combined to produce flexural behavior [57]. The top surface of the specimen is compressed at the loading point while the bottom surface is under tension. In compression scenarios, the imparted stress is easily transferred from the matrix to the GF across the interface. In the meanwhile, the GF inserted at the bottom of the composite sample successfully strengthened the sample under tension. The flexural modulus and the strength of HRS6 are reduced by 9.64 GPa and 182 MPa, respectively, when the hybrid is constructed with its highest number of layers. This is in line with the findings of most earlier studies [24,58].



Figure 7. Flexural properties of (a) rattan strips (RS) and (b) hybrid rattan (HRS) composites.

3.3. Impact Strength

Figure 8a,b illustrate the impact strength of pure and hybrid RS composites, respectively. In comparison, the configuration of all pure RS specimens is inferior to that of HRS. RS3 has a maximum impact absorption energy of 0.796 J. For the HRS, HRS5 has the highest impact absorption energy at 8.323 J. Other than that, the impact energy of pure RS had substantially risen when the number of layering configurations was increased from one to three. The maximum stacking concentration of RS4 reduces the impact energy by 0.640 J. A similar pattern was observed for HRS, in which the hybridization of three layers of rattan and two layers of GF at the outer surface significantly improved the maximum impact absorption energy.



Figure 8. Impact energy of (a) pure rattan strips (RS) and (b) hybrid rattan (HRS) composites.

When natural fibers are employed in a hybrid, the polymer composite's mechanical properties may be strengthened by introducing synthetic fibers, since synthetic fibers help compensate for natural fibers' limits. In hybrid composites, rattan fiber did not completely fracture because it was bonded between glass fibers (Figure 9). Due to the impact damage, the GF at the top was broken. The fiber cracked at various levels, indicating that a certain amount of energy was absorbed during fiber pull-out. The impact strength findings in this study are consistent with previous studies, which also revealed an increase in impact strength when using a GF hybrid with coir fiber to reinforce polyester composites [59]. Apart from that, the maximum configuration of HRS6's layering sequence reduced the impact energy to 6.465 J. Similar research by Ramnath et al. (2013) revealed that the impact energies of three-layer hybrids of jute and abaca with two plies of GF are 16 J and 15 J, respectively [24].



Figure 9. Impact fracture specimens of RS and HRS.

3.4. Thermogravimetric Analysis

Thermal analysis is a test that can be employed to assess the structural, chemical, and physical changes that occur in a material because of temperature changes. Temperature is an important state variable that influences most structural changes, chemical reactions, and physical qualities [45]. This study observed two different thermal analysis methods: thermogravimetric analysis (TGA) to measure weight loss with temperature change. Figure 10a,billustrate the graph of thermogravimetric analysis (TGA) and derivative thermogravimetry (DTG) on three samples that were selected based on the mechanical properties of virgin epoxy, RS3, and five layers of HRS with GF composites (HRS5). Thermal decomposition of the composites occurs between 30 and 700 °C. Additionally, Figure 10 portrays the percentage of mass temperature curves, demonstrating that adding pure RS3 and HRS5 in ER decreases the weight loss as a function of temperature. In contrast to other samples, RS3 lost weight at a lower temperature, approximately 4.5% of its initial weight, as shown in the graph, which is comparable to the loss of mass caused by the evaporation of the moisture in the rattan. In the meantime, the virgin epoxy and the HRS5 composite had weight drops of 1.2% and 0.6%, respectively. This is because the hemicellulose in the RS of the composite absorbs more moisture [60]. Figure 10 shows the DTG curves for the epoxy, HRS5, and RS3 samples. It is clear that the main peaks on the DTG curve indicate the maximum decomposition temperature (T_{max}) , which occurs at temperatures of 378.45, 367.19, and 369.87 °C for the epoxy, HRS5, and RS3 specimens, respectively. T_{max} refers to the degradation temperature showing the maximum weight loss. It also relates to the maximum decomposition temperature. Furthermore, T_{max} denotes an essential indicator showing the material's thermal stability [31].



Figure 10. TGA and DTG of virgin epoxy, RS3, and HRS5.

The results of this study clearly exhibit the effect of using RS and GF on the stability of epoxy composites, with T_{max} on epoxy being higher than RS3 and HRS5. The DTG curves on HRS5 and RS3 show a small shoulder peak before (200–300 °C) and after (about 500 °C) the main peak or T_{max} . These shoulder peaks are usually found in natural fiber composites. Note that the shoulders found between temperatures of 200 °C and 300 °C indicate the presence of hemicellulose, while a temperature of approximately 500 °C can be correlated with lignin decomposition. The decomposition of cellulose from natural fibers occurs at a temperature of about 370 °C, which is associated with the depolymerization and breaking of the epoxy molecular chains (350–400 °C) [61,62]. The findings of this research demonstrate that there is a main peak or T_{max} in the DTG curve, which is almost the same between the fiber and matrix.

Table 3 depicts the weight loss of the epoxy, HRS5, and RS3 by temperature change. Over the temperature range of 200–500 °C, it was possible to notice a mass loss of 73.96% in the RS3 composite. The degradation of the lignocellulosic components of the fiber, for instance, the lignin, hemicellulose, and cellulose constituents, may be responsible for the mass loss that occurs within this temperature range [63,64]. Between temperatures of 200 and 500 °C, virgin epoxy and HRS5 lost approximately 88.56% and 33.56% of their weight, respectively. Based on these observations, it is possible to deduce that adding GF to hybrid composites reduced the decomposition temperature [65]. The addition of GF successfully enhanced the composites' thermal stability. Identical outcomes were reported for the thermal decomposition of composites made of jute and GF [66]. This result is consistent with previous observations of a similar thermogravimetric trend for composites [67]. At the higher temperature setting of decomposition at 700 °C, it was observed that the char residue of HRS5 composites is the highest compared to those of RS3 and virgin epoxy. According to the findings, while GF hybridization increased both of the hybrid composites' initial and final decomposition temperatures, their thermal stability improved. Similar conclusions were reported by Ghani et al. [47] in their investigation into the performance of jute/GF with different layering configurations.

Temperature (°C)	Weight Loss (%)		
	Epoxy	HRS5	RS3
25-200	0.95	0.75	5.54
200-500	88.56	33.56	73.96

Table 3. The weight loss of epoxy, HRS5, and RS3 by temperature change.

3.5. Differential Scanning Calorimetry (DSC)

Figure 11 depicts the DSC curve for the epoxy, HRS5, and RS3 specimens. The DSC curve showed the chemical and thermal response of the fibers as the temperature rose. Meanwhile, endothermic peaks in the temperature range of 30 to 175 °C are seen in the HRS5 and RS3 specimens, confirming the existence of water molecules. The occurrence of peaks at 67.28 °C and 173.48 °C in this investigation demonstrated the existence of water molecules in HRS5. The occurrence of peaks at 69.18 °C and 172 °C in RS3 specimens, on the other hand, indicated the existence of water molecules. The epoxy, HRS5, and RS3 specimens were stable between these temperatures, since no endothermic or exothermic reactions were seen in the 80 to 160 °C range [31,68]. Hence, data from the literature indicate that hemicellulose thermal decomposition starts at around 180 °C and concludes at around 350 °C [31,69]. As shown in Figure 11 the decomposition of the hemicellulose on the HRS5 and RS3 occurs at temperatures of 254.46 °C and 204.26 °C, respectively.



Figure 11. DSC curves of pure epoxy, RS3, and HRS5.

4. Conclusions

Analysis was done on the thermal and mechanical properties of hybrid and pure epoxy composites reinforced with rattan strips (RS). What happens when glass fiber (GF) is stacked with rattan and hybrid rattan was identified. The tensile, flexural, and impact strengths of a pure rattan-reinforced epoxy composite grew as the stacking number rises, according to the composite's mechanical properties. In addition, three layers of woven rattan showed the highest mechanical properties when contrasted with the other configurations. The hybrid rattan and GF showed that the combination of three layers of RS and two plies of GF increases the mechanical significantly. The thermal properties of the selected materials, including virgin epoxy, RS3, and HRS5, were assessed by employing thermogravimetric analysis (TGA) and differential scanning calorimetry (DSC). Here, the high decomposition temperature revealed that the RS and GF hybridization is more thermally stable. The hybridization of rattan with GF has effectively enhanced the mechanical properties and thermal properties of the composites compared to pure rattan. Therefore, it is feasible to conclude that hybridization is a method for enhancing the strength, modulus, energy absorption, and thermal stability of polymeric composites. Moreover, the findings of this study indicate that the hybridization of a rattan/GF-reinforced epoxy composite possesses the potential to be utilized in automobile bumper beams.

Author Contributions: Conceptualization, A.P.I.; Methodology, M.Z.A. and D.F.F.; Validation, A.E.H. and J.J.; Formal Analysis, D.F.F., A.E.H. and T.R.; Investigation, J.P.S.; Resources, D.W.U. and N.N.; Data Curation, N.N. and T.R.; Writing—Original Draft Preparation, J.P.S. and T.C.; Writing—Review & Editing, T.C. and M.Z.A.; Visualization, J.J., D.W.U. and P.T.A.; Project Administration, P.T.A.; Funding Acquisition, A.P.I. All authors have read and agreed to the published version of the manuscript.

Funding: This study was funded by the Ministry of Education, Culture, Research, and Technology of the Republic of Indonesia and Universitas Tarumanagara, through Grant No. 470/LL3/AK.04/2022 and Contract No. 0800-Int-KLPPM/UNTAR/VI/2022.

Institutional Review Board Statement: Not applicable.

Informed Consent Statement: Not applicable.

Data Availability Statement: Data are contained within the article.

Acknowledgments: The authors would like to thank the Ministry of Education, Culture, Research, and Technology of the Republic of Indonesia and Universitas Tarumanagara for the PTUPT Research Grant, in 2022, and Universiti Malaysia Pahang for providing equipment for the research data collection.

Conflicts of Interest: The authors declare no conflict of interest.

References

- 1. Ahmed, K.S.; Vijayarangan, S.; Kumar, A. Low Velocity Impact Damage Characterization of Woven Jute—Glass Fabric Reinforced Isothalic Polyester Hybrid Composites. J. Reinf. Plast. Compos. 2007, 26, 959–976. [CrossRef]
- Aisyah, H.A.; Paridah, M.T.; Sapuan, S.M.; Ilyas, R.A.; Khalina, A.; Nurazzi, N.M.; Lee, S.H.; Lee, C.H. A Comprehensive Review on Advanced Sustainable Woven Natural Fibre Polymer Composites. *Polymers* 2021, 13, 471. [CrossRef] [PubMed]
- Alavudeen, A.; Rajini, N.; Karthikeyan, S.; Thiruchitrambalam, M.; Venkateshwaren, N. Mechanical Properties of Banana/Kenaf Fiber-Reinforced Hybrid Polyester Composites: Effect of Woven Fabric and Random Orientation. *Mater. Des.* 2015, 66, 246–257. [CrossRef]
- 4. Rajesh, M.; Pitchaimani, J. Mechanical Properties of Natural Fiber Braided Yarn Woven Composite: Comparison with Conventional Yarn Woven Composite. *J. Bionic Eng.* 2017, *14*, 141–150. [CrossRef]
- Tezara, C.; Hadi, A.E.; Siregar, J.P.; Muhamad, Z.; Hamdan, M.H.M.; Oumer, A.N.; Jaafar, J.; Irawan, A.P.; Rihayat, T.; Fitriyana, D.F. The Effect of Hybridisation on Mechanical Properties and Water Absorption Behaviour of Woven Jute/Ramie Reinforced Epoxy Composites. *Polymers* 2021, 13, 2964. [CrossRef] [PubMed]
- Tezara, C.; Zalinawati, M.; Siregar, J.P.; Jaafar, J.; Hamdan, M.H.M.; Oumer, A.N.; Chuah, K.H. Effect of Stacking Sequences, Fabric Orientations, and Chemical Treatment on the Mechanical Properties of Hybrid Woven Jute–Ramie Composites. *Int. J. Precis. Eng. Manuf. -Green Technol.* 2022, 9, 273–285. [CrossRef]
- Misnon, M.I.; Islam, M.M.; Epaarachchi, J.A.; Lau, K.T. Analyses of Woven Hemp Fabric Characteristics for Composite Reinforcement. *Mater. Des.* 2015, 66, 82–92. [CrossRef]
- Azlin, M.N.M.; Sapuan, S.M.; Zuhri, M.Y.M.; Zainudin, E.S.; Ilyas, R.A. Thermal Stability, Dynamic Mechanical Analysis and Flammability Properties of Woven Kenaf/Polyester-Reinforced Polylactic Acid Hybrid Laminated Composites. *Polymers* 2022, 14, 2690. [CrossRef]
- Jawaid, M.; Khalil, H.P.S.A. Cellulosic/Synthetic Fibre Reinforced Polymer Hybrid Composites: A Review. *Carbohydr. Polym.* 2011, 86, 1–18. [CrossRef]
- 10. Adesina, O.T.; Jamiru, T.; Sadiku, E.R.; Ogunbiyi, O.F.; Beneke, L.W. Mechanical Evaluation of Hybrid Natural Fibre–Reinforced Polymeric Composites for Automotive Bumper Beam: A Review. *Int. J. Adv. Manuf. Technol.* **2019**, *103*, 1781–1797. [CrossRef]
- 11. Dong, C. Review of Natural Fibre-Reinforced Hybrid Composites. J. Reinf. Plast. Compos. 2018, 37, 331–348. [CrossRef]
- 12. Davoodi, M.M.; Sapuan, S.M.; Ahmad, D.; Aidy, A.; Khalina, A.; Jonoobi, M. Concept Selection of Car Bumper Beam with Developed Hybrid Bio-Composite Material. *Mater. Des.* **2011**, *32*, 4857–4865. [CrossRef]
- 13. Muthalagu, R.; Murugesan, J.; Kumar, S.S.; Babu, B.S. Tensile Attributes and Material Analysis of Kevlar and Date Palm Fibers Reinforced Epoxy Composites for Automotive Bumper Applications. *Mater. Today Proc.* **2021**, *46*, 433–438. [CrossRef]
- Safri, S.N.A.; Sultan, M.T.H.; Jawaid, M.; Jayakrishna, K. Impact Behaviour of Hybrid Composites for Structural Applications: A Review. Compos. B Eng. 2018, 133, 112–121. [CrossRef]
- 15. Zhang, Y.; Li, Y.; Ma, H.; Yu, T. Tensile and Interfacial Properties of Unidirectional Flax/Glass Fiber Reinforced Hybrid Composites. *Compos. Sci. Technol.* **2013**, *88*, 172–177. [CrossRef]
- Davoodi, M.M.; Sapuan, S.M.; Ahmad, D.; Ali, A.; Khalina, A.; Jonoobi, M. Mechanical Properties of Hybrid Kenaf/Glass Reinforced Epoxy Composite for Passenger Car Bumper Beam. *Mater. Des.* 2010, 31, 4927–4932. [CrossRef]
- 17. Atiqah, A.; Maleque, M.A.; Jawaid, M.; Iqbal, M. Development of Kenaf-Glass Reinforced Unsaturated Polyester Hybrid Composite for Structural Applications. *Compos. B Eng.* **2014**, *56*, 68–73. [CrossRef]
- Ramasubbu, R.; Madasamy, S. Fabrication of Automobile Component Using Hybrid Natural Fiber Reinforced Polymer Composite. J. Nat. Fibers 2022, 19, 736–746. [CrossRef]
- Sapuan, S.M.; Maleque, M.A.; Hameedullah, M.; Suddin, M.N.; Ismail, N. A Note on the Conceptual Design of Polymeric Composite Automotive Bumper System. J. Mater. Process. Technol. 2005, 159, 145–151. [CrossRef]
- 20. Olorunnishola, A.A.G.; Adubi, E.G. A Comparative Analysis of a Blend of Natural Jute and Glass Fibers with Synthetic Glass Fibers Composites as Car Bumper Materials. *IOSR J. Mech. Civ. Eng.* **2018**, *15*, 67–71.

- Maisuriya, V.; Jain, P.; Jariwala, H.; Badagha, D. Analysis of Unidirectional Aligned Banana and Glass Fibre Reinforced Polyester Composite for Tensile and Flexural Strength. J. Polym. Compos. 2020, 8, 49–61.
- Santhanam, V.; Dhanaraj, R.; Chandrasekaran, M.; Venkateshwaran, N.; Baskar, S. Experimental Investigation on the Mechanical Properties of Woven Hybrid Fiber Reinforced Epoxy Composite. *Mater. Today Proc.* 2021, 37, 1850–1853.
- Gujjala, R.; Ojha, S.; Acharya, S.K.; Pal, S.K. Mechanical Properties of Woven Jute–Glass Hybrid-Reinforced Epoxy Composite. J. Compos. Mater. 2014, 48, 3445–3455. [CrossRef]
- Ramnath, B.V.; Kokan, S.J.; Raja, R.N.; Sathyanarayanan, R.; Elanchezhian, C.; Prasad, A.R.; Manickavasagam, V.M. Evaluation of Mechanical Properties of Abaca–Jute–Glass Fibre Reinforced Epoxy Composite. *Mater. Des.* 2013, 51, 357–366. [CrossRef]
- Kumar, K.S.; Siva, I.; Rajini, N.; Jappes, J.T.W.; Amico, S.C. Layering Pattern Effects on Vibrational Behavior of Coconut Sheath/Banana Fiber Hybrid Composites. *Mater. Des.* 2016, 90, 795–803. [CrossRef]
- 26. Bhoopathi, R.; Ramesh, M.; Deepa, C. Fabrication and Property Evaluation of Banana-Hemp-Glass Fiber Reinforced Composites. *Procedia Eng.* **2014**, *97*, 2032–2041. [CrossRef]
- Acharya, S.K. Soma Dalbehera Study on Mechanical Properties of Natural Fiber Reinforced Woven Jute-Glass Hybrid Epoxy Composites. *Adv. Polym. Sci. Technol.* 2014, 4, 1–6.
- Yahaya, R.; Sapuan, S.M.; Jawaid, M.; Leman, Z.; Zainudin, E.S. Effect of Layering Sequence and Chemical Treatment on the Mechanical Properties of Woven Kenaf–Aramid Hybrid Laminated Composites. *Mater. Des.* 2015, 67, 173–179. [CrossRef]
- 29. Rajesh, M.; Singh, S.P.; Pitchaimani, J. Mechanical Behavior of Woven Natural Fiber Fabric Composites: Effect of Weaving Architecture, Intra-Ply Hybridization and Stacking Sequence of Fabrics. *J. Ind. Text.* **2018**, *47*, 938–959. [CrossRef]
- 30. Elakhame, Z.U.; Alhassan, O.A.; Samuel, A.E. Development and Production of Brake Pads from Palm Kernel Shell Composites. *Int. J. Sci. Eng. Res.* **2014**, *5*, 735–744.
- Cionita, T.; Siregar, J.P.; Shing, W.L.; Hee, C.W.; Fitriyana, D.F.; Jaafar, J.; Junid, R.; Irawan, A.P.; Hadi, A.E. The Influence of Filler Loading and Alkaline Treatment on the Mechanical Properties of Palm Kernel Cake Filler Reinforced Epoxy Composites. *Polymers* 2022, 14, 3063. [CrossRef] [PubMed]
- 32. Gu, Y.; Zhang, J. Tensile Properties of Natural and Synthetic Rattan Strips Used as Furniture Woven Materials. *Forests* **2020**, 11, 1299. [CrossRef]
- 33. Nath, A.; Kanjilal, T.; Bhattacharjee, C. Application of Bioactive Composite Green Polymer for the Development of Artificial Organs. In *New Polymeric Composite Materials*; Materials Research Forum LLC: Millersville, PA, USA, 2016.
- Abasolo, W.P. Properties of Rattan Cane as Basis for Determining Optimum Cutting Cycle of Cultivated Calamus Merrillii. J. Trop. For. Sci. 2015, 27, 176–188.
- Rachchh, N.V.; Ujeniya, P.S.; Misra, R.K. Mechanical Characterisation of Rattan Fibre Polyester Composite. *Procedia Mater. Sci.* 2014, 6, 1396–1404. [CrossRef]
- Li, K.; Zhao, R.; Xia, J.; Zhao, G.-L. Reinforcing Microwave Absorption Multiwalled Carbon Nanotube–Epoxy Composites Using Glass Fibers for Multifunctional Applications. *Adv. Eng. Mater.* 2020, 22, 1900780. [CrossRef]
- Ochi, S. Mechanical Properties of Bamboo Fiber Bundle-Reinforced Bamboo Powder Composite Materials. *Eur. J. Wood Wood Prod.* 2022, 80, 263–275. [CrossRef]
- Ramanaiah, K.; Prasad, A.V.R.; Chandra Reddy, K.H. Mechanical and Thermo-Physical Properties of Fish Tail Palm Tree Natural Fiber–Reinforced Polyester Composites. Int. J. Polym. Anal. Charact. 2013, 18, 126–136. [CrossRef]
- 39. Sharba, M.J.; Leman, Z.; Sultan, M.T.; Ishak, M.R.; Hanim, M.A.A. Partial Replacement of Glass Fiber by Woven Kenaf in Hybrid Composites and Its Effect on Monotonic and Fatigue Properties. *Bioresources* **2016**, *11*, 2665–2683. [CrossRef]
- Irawan, A.P.; Sukania, I.W. Tensile Strength of Car Spoiler Product Based on ABS Plastic and Rattan Fiber Epoxy Composite Materials. In Proceedings of the 3rd Nommensen International Conference on Technology and Engineering 2019 (3rd NICTE), Nommensen HKBP University, Nommensen, Indonesia, 25–26 July 2019; Volume 725, p. 012040.
- Karthick, M.; Meikandan, M.; Kaliappan, S.; Karthick, M.; Sekar, S.; Patil, P.P.; Raja, S.; Natrayan, L.; Paramasivam, P. Experimental Investigation on Mechanical Properties of Glass Fiber Hybridized Natural Fiber Reinforced Penta-Layered Hybrid Polymer Composite. Int. J. Chem. Eng. 2022, 1–9. [CrossRef]
- Azlin, M.N.M.; Sapuan, S.M.; Zuhri, M.Y.M.; Zainudin, E.S. Effect of Stacking Sequence and Fiber Content on Mechanical and Morphological Properties of Woven Kenaf/Polyester Fiber Reinforced Polylactic Acid (PLA) Hybrid Laminated Composites. J. Mater. Res. Technol. 2022, 16, 1190–1201. [CrossRef]
- Nair, A.B.; Joseph, R. Eco-Friendly Bio-Composites Using Natural Rubber (NR) Matrices and Natural Fiber Reinforcements. In *Chemistry, Manufacture and Applications of Natural Rubber*; Elsevier: Amsterdam, The Netherlands, 2014; pp. 249–283.
- 44. Jegan, M.M.; Sathishkumar, T.P.; Anand, V.; Arun Ganesh, R.; Logesh Raja, C.; Mohanraj, K. Investigation of Fracture Behavior on Glass & Natural Fibre Reinforced Epoxy Composites. *Int. J. Eng. Res. Technol.* **2019**, *7*, 13–17.
- Nurazzi, N.M.; Asyraf, M.R.M.; Fatimah Athiyah, S.; Shazleen, S.S.; Rafiqah, S.A.; Harussani, M.M.; Kamarudin, S.H.; Razman, M.R.; Rahmah, M.; Zainudin, E.S. A Review on Mechanical Performance of Hybrid Natural Fiber Polymer Composites for Structural Applications. *Polymers* 2021, 13, 2170. [CrossRef] [PubMed]
- 46. Ismail, M.; Rejab, M.R.M.; Siregar, J.P.; Mohamad, Z.; Quanjin, M.; Mohammed, A.A. Mechanical Properties of Hybrid Glass Fiber/Rice Husk Reinforced Polymer Composite. *Mater. Today Proc.* **2020**, *27*, 1749–1755. [CrossRef]

- Ghani, M.U.; Siddique, A.; Abraha, K.G.; Yao, L.; Li, W.; Khan, M.Q.; Kim, I.-S. Performance Evaluation of Jute/Glass-Fiber-Reinforced Polybutylene Succinate (PBS) Hybrid Composites with Different Layering Configurations. *Materials* 2022, 15, 1055. [CrossRef]
- 48. Hariharan, A.B.A.; Khalil, H.P.S.A. Lignocellulose-Based Hybrid Bilayer Laminate Composite: Part I-Studies on Tensile and Impact Behavior of Oil Palm Fiber-Glass Fiber-Reinforced Epoxy Resin. J. Compos. Mater. 2005, 39, 663–684. [CrossRef]
- 49. Wang, R.; Tian, G.; Yang, S.; Wang, Y.; Jiang, Z. Tensile Properties of Single Rattan Fibers. Wood Fiber Sci. 2014, 46, 519–526.
- 50. Suriani, M.J.; Rapi, H.Z.; Ilyas, R.A.; Petrů, M.; Sapuan, S.M. Delamination and Manufacturing Defects in Natural Fiber-Reinforced Hybrid Composite: A Review. *Polymers* **2021**, *13*, 1323. [CrossRef]
- Selver, E.; Dalfi, H.; Yousaf, Z. Investigation of the Impact and Post-Impact Behaviour of Glass and Glass/Natural Fibre Hybrid Composites Made with Various Stacking Sequences: Experimental and Theoretical Analysis. J. Ind. Text. 2022, 51, 1264–1294. [CrossRef]
- 52. Sanjay, M.R.; Arpitha, G.R.; Yogesha, B. Study on Mechanical Properties of Natural-Glass Fibre Reinforced Polymer Hybrid Composites: A Review. *Mater. Today Proc.* 2015, *2*, 2959–2967. [CrossRef]
- 53. Gowda, T.M.; Naidu, A.C.B.; Chhaya, R. Some Mechanical Properties of Untreated Jute Fabric-Reinforced Polyester Composites. *Compos. Part A Appl. Sci. Manuf.* **1999**, *30*, 277–284. [CrossRef]
- 54. Sreekala, M.S.; George, J.; Kumaran, M.G.; Thomas, S. The Mechanical Performance of Hybrid Phenol-Formaldehyde-Based Composites Reinforced with Glass and Oil Palm Fibres. *Compos. Sci. Technol.* **2002**, *62*, 339–353. [CrossRef]
- 55. Ho, M.; Lau, K. Design of an Impact Resistant Glass Fibre/Epoxy Composites Using Short Silk Fibres. *Mater. Des.* 2012, 35, 664–669. [CrossRef]
- 56. Saha, N.; Banerjee, A.N.; Mitra, B.C. Tensile Behaviour of Unidirectional Polyethylene-Glass Fibres/PMMA Hybrid Composite Laminates. *Polymer* **1996**, *37*, 699–701. [CrossRef]
- 57. Ma, W.; Elkin, R. Characterizations of Sandwich Structures. In *Sandwich Structural Composites*; CRC Press: Boca Raton, FL, USA, 2021; pp. 185–252. ISBN 100303537X.
- Megahed, M.; Ali-Eldin, S.S.; Abd El Moezz, S.M.; Abdalla, W.S. Synthesis of Developed Rice Straw Sheets and Glass Fiber-Reinforced Polyester Composites. J. Compos. Mater. 2020, 54, 3381–3394. [CrossRef]
- Jayabal, S.; Natarajan, U.; Sathiyamurthy, S. Effect of Glass Hybridization and Staking Sequence on Mechanical Behaviour of Interply Coir–Glass Hybrid Laminate. *Bull. Mater. Sci.* 2011, 34, 293–298. [CrossRef]
- 60. Ridzuan, M.J.M.; Majid, M.S.A.; Afendi, M.; Mazlee, M.N.; Gibson, A.G. Thermal Behaviour and Dynamic Mechanical Analysis of Pennisetum Purpureum/Glass-Reinforced Epoxy Hybrid Composites. *Compos. Struct.* **2016**, *152*, 850–859. [CrossRef]
- 61. Ramesh, V.; Anand, P. Thermal Analysis of Kevlar/Basalt Reinforced Hybrid Polymer Composite. *Mater. Res. Express* 2021, *8*, 115302. [CrossRef]
- Ferreira, M.V.F.; Neves, A.C.C.; de Oliveira, C.G.; Lopes, F.P.D.; Margem, F.M.; Vieira, C.M.F.; Monteiro, S.N. Thermogravimetric Characterization of Polyester Matrix Composites Reinforced with Eucalyptus Fibers. *J. Mater. Res. Technol.* 2017, *6*, 396–400. [CrossRef]
- 63. Shahinur, S.; Hasan, M.; Ahsan, Q.; Saha, D.K.; Islam, M. Characterization on the Properties of Jute Fiber at Different Portions. *Int. J. Polym. Sci.* 2015, 2015, 262348. [CrossRef]
- 64. Lubis, M.A.R.; Handika, S.O.; Sari, R.K.; Iswanto, A.H.; Antov, P.; Kristak, L.; Lee, S.H.; Pizzi, A. Modification of Ramie Fiber via Impregnation with Low Viscosity Bio-Polyurethane Resins Derived from Lignin. *Polymers* **2022**, *14*, 2165. [CrossRef]
- 65. Atiqah, A.; Jawaid, M.; Sapuan, S.M.; Ishak, M.R.; Alothman, O.Y. Thermal Properties of Sugar Palm/Glass Fiber Reinforced Thermoplastic Polyurethane Hybrid Composites. *Compos. Struct.* **2018**, *202*, 954–958. [CrossRef]
- Braga, R.A.; Magalhaes, P.A.A., Jr. Analysis of the Mechanical and Thermal Properties of Jute and Glass Fiber as Reinforcement Epoxy Hybrid Composites. *Mater. Sci. Eng. C* 2015, *56*, 269–273. [CrossRef] [PubMed]
- AlMaadeed, M.A.; Kahraman, R.; Khanam, P.N.; Madi, N. Date Palm Wood Flour/Glass Fibre Reinforced Hybrid Composites of Recycled Polypropylene: Mechanical and Thermal Properties. *Mater. Des.* 2012, 42, 289–294. [CrossRef]
- Sinha, E.; Rout, S.K. Influence of Fibre-Surface Treatment on Structural, Thermal and Mechanical Properties of Jute Fibre and Its Composite. Bull. Mater. Sci. 2009, 32, 65–76. [CrossRef]
- 69. Bryś, A.; Bryś, J.; Ostrowska-Ligęza, E.; Kaleta, A.; Górnicki, K.; Głowacki, S.; Koczoń, P. Wood Biomass Characterization by DSC or FT-IR Spectroscopy. *J. Therm. Anal. Calorim.* **2016**, *126*, 27–35. [CrossRef]

Polymers

also developed by scimago:

SCIMAGO INSTITUTIONS RANKINGS

and the second second	A 100	

Home

Journal Rankings Co

Country Rankings Viz Tools

About Us

Enter Journal Title, ISSN or Publisher Name

Help

Polymers 👌

COUNTRY	SUBJECT AREA AND CATEGORY	PUBLISHER	H-INDEX
Switzerland Universities and research institutions in Switzerland	Chemistry Chemistry (miscellaneous) Materials Science Polymers and Plastics	MDPI AG	89
PUBLICATION TYPE	ISSN	COVERAGE	INFORMATION
Journals	20734360	1969, 2009-2021	Homepage
			How to publish in this journal
			alboeker@uni- potsdam.de

Ad closed by Google

Ad closed by Google

SCOPE

-Polymer Synthesis: synthesis of copolymers, block-polymers, polyesters, elastomer, polyolefins, polyamides, polycarbonates, rubber, thermoplastics, thermosets, methods for polymerization, etc. -Polymer Analysis: characterization and analysis of polymers, polymeric materials and polymer additives, polymerization mechanism, measurement of molecular weight, size, conformation, structure, properties and behavior of polymers, separation, spectroscopy, and scattering techniques, structure-property-processing relationships. -Polymer Physics: crystallization, rheology, swelling, phase separation, viscosity and viscoelasticity, entanglements and crosslinking, mechanical properties, dielectric properties, optical properties, thermal properties, the kinetics of degradation and polymerization, polymers subjected to deformation, flow, and other external fields, polymers at interfaces and in confined spaces. -Polymer Theory and Simulation: numerical simulation for macromolecular systems towards the understanding of underlying physical or physico-chemical mechanisms, modeling of polymer structure and conformation, predictive algorithms of polymers, constitutive and multiscale modeling approaches for polymeric systems, kinetic theory of polymers, artificial intelligence, machine learning and data-driven modeling of polymers. -Polymer Processing and Performance: thermoforming, compression and transfer molding, rotational molding, extrusion, injection molding, blow molding, plastic foam molding. -Polymer Applications[...] -Biobased and Biodegradable Polymers[...] -Polymer Recycling[...] -Polymer Composites and Nanocomposites[...]

 \bigcirc Join the conversation about this journal

Ad closed by Google

Quartiles
 ☐



https://www.scimagojr.com/journalsearch.php?q=54222&tip=sid&clean=0



Polymers





Explore, visually communicate and make sense of data with our new data visualization tool.





← Show this widget in your own website

> Just copy the code below and paste within your html code:

<a href="https://www.scimaç

CAS NO: 68953-84-4

Metrics based on Scopus® data as of April 2022

Н

Hay 2 years ago

Hello, please the rating of this journal in 2019 and 2020 is Q1, is there a way to know the rating in 2021, is it still Q1?

reply



Melanie Ortiz 2 years ago

SCImago Team

Dear Hay,

Thank you for contacting us. Our data come from Scopus, they annually send us an update of the data. This update is sent to us around April / May every year. The SJR for 2020 has been released on 17 May 2021. Therefore, the indicators for 2021 will be available in May/June 2022 and before that date we can't know what will happen with this journal. Best Regards, SCImago Team

Brought to you by Universiti Putra Malaysia



Source details

Polymers	CiteScore 2021 5 7	()
Open Access ()	J./	
Scopus coverage years: from 2009 to Present		
Publisher: Multidisciplinary Digital Publishing Institute (MDPI)	SJR 2021	(i)
E-ISSN: 2073-4360	0.726	-
Subject area: (Materials Science: Polymers and Plastics) (Chemistry: General Chemistry)		
Source type: Journal	SNIP 2021	(i)
	1.170	· ·
View all documents > Set document alert 🛛 🖽 Save to source list 📄 Locate full-text(opens in a new window)		

CiteScore CiteScore rank & trend

Scopus content coverage

Year	Documents published	Actions
2022	5,325 documents	View citation overview >
2021	4,446 documents	View citation overview >
2020	3,063 documents	View citation overview >
2019	2,125 documents	View citation overview >
2018	1,412 documents	View citation overview >
2017	729 documents	View citation overview >
2016	439 documents	View citation overview >
2015	149 documents	View citation overview >
2014	162 documents	View citation overview >
2013	57 documents	View citation overview >
2012	79 documents	View citation overview >
2011	124 documents	View citation overview >
2010	44 documents	View citation overview >
2009	3 documents	View citation overview >

Q